

AD-A047 878

CASE WESTERN RESERVE UNIV CLEVELAND OHIO DEPT OF CHEMISTRY F/G 7/2
A SERIES OF 'TERT'-BUTYLDIMETHYLSILOXANES OF INCREASING STERIC --ETC(U)
DEC 77 G W RITTER, M E KENNEY N00014-75-C-0693

UNCLASSIFIED

TR-4

NL

| OF |
AD
A047878



END
DATE
FILMED
1 -78
DDC

AD A 047878

12
52

15 Office of Naval Research
Contract No. N00014-75-C-0693
9 Project No. NR-356-590
Technical Report No. 4

14 TIR-4

6 A SERIES OF tert-BUTYLDIMETHYLSILOXANES OF
INCREASING STERIC HINDRANCE.

10 by
George W./Ritter, II and Malcolm E./Kenney

Chemistry Department
Case Western Reserve University
Cleveland, Ohio 44106

11 9 December 9, 1977

12 9p.

DDC
RECEIVED
DEC 19 1977
E

Reproduction in whole or in part is permitted for any purpose
of the United States Government

Approved for Public Release; Distribution Unlimited

AD No. —
DDC FILE COPY

1472
404 239

1B

A SERIES OF tert-BUTYLDIMETHYLSILOXANES OF INCREASING STERIC
HINDRANCE

George W. Ritter, II and Malcolm E. Kenney*

Chemistry Department
Case Western Reserve University
Cleveland, Ohio 44106

SUMMARY

Reaction of bis(dimethylsilyl)acetamide with tert-butyl-dimethylsilanol has been found to give 1-tert-butyl-1,1,3,3-tetramethyldisiloxane while reaction of bis(trimethylsilyl)-acetamide or trimethylchlorosilane with this silanol has been found to give 1-tert-butyl-1,1,3,3,3-pentamethyldisiloxane. Similarly, reaction of tert-butyldimethylchlorosilane with this silanol has been found to produce 1,3-di-tert-butyl-1,1,3,3-tetramethyldisiloxane and reaction of tert-butyldimethylchlorosilane with phthalocyaninosilanediol has been found to produce 1,5-tert-butyl-1,1,5,5-tetramethyl-3-phthalocyanino-trisiloxane. This last siloxane is noteworthy because it is highly hindered.

INTRODUCTION

A number of years ago Sommer and Tyler reported tert-butyldimethylchlorosilane. Recently this compound has attracted considerable attention because, as Corey has shown, it is a very effective blocking agent for hydroxyl groups in organic intermediates.

The silanol corresponding to this chlorosilane, tert-butyldimethylsilanol, was also reported by Sommer and Tyler, but uses for it have not been found and it has attracted

ACCESSION for	
NTIS	White Section <input checked="" type="checkbox"/>
DDC	Buff Section <input type="checkbox"/>
UNANNOUNCED	<input type="checkbox"/>
JUSTIFICATION	
BY	
DISTRIBUTION/AVAILABILITY	
DI	and/or
A	

little attention. This compound is an interesting one nevertheless. It reacts with water very readily to form a hemihydrate (as does the corresponding carbinol, tert-butyl-dimethylcarbinol^x), and, more significantly, it does not self-condense on being heated to fairly high temperatures.

The symmetrical siloxane of this series, 1,3-di-tert-butyl-1,1,3,3-tetramethyldisiloxane, has not been reported although Sommer and Tyler attempted to prepare it from the silanol (i.e., tert-butyldimethylsilanol) with the aid of sulfuric acid and with the aid of iodine. These workers did imply, however, that while hindered this compound could well be synthesizable.

Unsymmetrical siloxanes of this series also have not been reported, apparently.

Recently an interest in siloxanes of this general type in this laboratory has led to work on some of them. This has yielded a series of tert-butyldimethylsiloxanes having differing amounts of steric hindrance.

RESULTS AND DISCUSSION

Two of these siloxanes are 1-tert-butyl-1,1,3,3-tetramethyldisiloxane and 1-tert-butyl-1,1,3,3,3-pentamethyldisiloxane. The first of these has been prepared by the reaction of bis(dimethylsilyl)acetamide with tert-butyldimethylsilanol. The second has been prepared by the reaction of bis(trimethylsilyl)acetamide with the silanol and also by the reaction of trimethylchlorosilane with the silanol. Since these compounds are relatively unhindered, the fact that they can be made is not surprising. Further, the fact that they can be made by the routes used is likewise not surprising because these are of standard types.

Another of these siloxanes is the already mentioned 1,3-di-tert-butyl-1,1,3,3-tetramethyldisiloxane. This has been

prepared by the reaction of tert-butyldimethylchlorosilane with tert-butyldimethylsilanol. In keeping with its preparability, as already mentioned, is the viewpoint implied by Sommer and Tyler.

Still another is 1,5-tert-butyl-1,1,5,5-tetramethyl-3-phthalocyaninotrisiloxane. This compound has been prepared by the reaction of tert-butyldimethylchlorosilane with phthalocyaninosilanediol. It is of interest because it is so highly hindered. Without doubt rotation about its terminal O-Si bonds is severely limited. The route used to prepare it is noteworthy only in that it is simple and straightforward.

From this it is clear that many tert-butylmethylsiloxanes can be made. Further, it is clear that in general they will be stable and easy to handle.

EXPERIMENTAL

Spectra

The nmr spectra were taken with the aid of a Varian HA-100 instrument operating in FT mode. Tetramethylsilane was used as an internal standard for the phthalocyaninosiloxane. Chloroform was used as an internal standard for the remaining compounds.

t-BuMe₂SiOSiMe₂H

A mixture of bis(dimethylsilyl)acetamide (0.7 ml), tert-butyldimethylsilanol (1.0 ml), and dry pyridine (20 ml) was refluxed with stirring and protection from atmospheric moisture for 3 hr. The product was distilled and nearly all of the 108-115°C fraction was set aside for 3 weeks (during this time it separated into two fractions). It was then mixed with water (20 ml) and the resultant was extracted once with hexane (15 ml). After being dried (CaCl₂) and filtered, the hexane layer

was distilled to a head temperature of 120°C. The liquid remaining (~ 0.7 ml) was retained and a portion of it was chromatographed at 100°C on a 10% SE-30 Chromosorb W column. The major component, which was a colorless liquid and constituted about 75% of the total, was the siloxane. NMR (CDCl₃): δ 0.02 (s, SiMe₂t-Bu), 0.15 (d, SiMe₂H), 0.86 (s, SiMe₂t-Bu), and 4.69 ppm (m, SiMe₂H).

t-BuMe₂SiOSiMe₃

Trimethylchlorosilane (1.5 ml) was added with stirring to a dry solution of tri-n-butylamine (3 ml) and dimethylformamide (15 ml). tert-Butyldimethylsilanol (1.0 ml) was added after a minute and the mixture was refluxed with stirring and protection from atmospheric moisture for 3 hr. The product when cool was mixed with water (20 ml) and extracted once with hexane (15 ml). After being dried (CaCl₂) and filtered, the hexane layer was distilled. The 130-135°C fraction (~ 1 ml) was retained and a portion of it was chromatographed at 125°C as above. The major component, about 65% of the total, was the siloxane. It was a colorless liquid. NMR (CDCl₃): δ 0.03 (s, SiMe₂t-Bu), 0.09 (s, SiMe₃), and 0.88 ppm (s, SiMe₂t-Bu).

Anal. Calcd. for C₉H₂₄OSi₂: C, 52.87; H, 11.83; Si, 27.47. Found: C, 52.84; H, 11.89; Si, 27.20.

The siloxane was also prepared by reacting bis(trimethylsilyl)acetamide with tert-butyldimethylsilanol in refluxing pyridine.

t-BuMe₂OSiMe₂t-Bu

A solution of imidazole (1 g) and pyridine (25 ml) was dried by distilling off a small amount of it (~ 5 ml) and cooled. tert-Butyldimethylchlorosilane (1.2 g) and tert-butyldimethylsilanol (1.0 ml) were added and the mixture was

refluxed with stirring and protection from atmospheric moisture for 3 hr. and cooled. The product was mixed with water (20 ml) and the resultant was extracted once with hexane (15 ml). After being dried (CaCl_2) the hexane layer was filtered and distilled to a head temperature of 148°C . The liquid remaining (~ 0.4 ml) was retained and a portion of it was chromatographed at 175°C . The major component, a colorless fairly mobile liquid constituting about 85% of the total, proved to be the siloxane. NMR (CDCl_3): δ 0.01 (s, Me), and 0.87 ppm (s, t-Bu).

Anal. Calcd. for $\text{C}_{12}\text{H}_{30}\text{OSi}_2$: C, 58.46; H, 12.26; Si, 22.78. Found: C, 58.70; H, 12.05; Si, 22.64.

The siloxane was also synthesized both by refluxing the chlorosilane in wet pyridine and by refluxing it in pyridine exposed to moist air.

(t-BuMe₂SiO)₂SiPc

A mixture of tert-butyldimethylchlorosilane (1.0 g), phthalocyaninosilanediol (prepared by Douglass' procedure⁵) (0.43 g), dry tri-n-butylamine (15 ml), and distilled, dry, nitrogen-purged quinoline (30 ml) was refluxed with stirring and protection from atmospheric moisture for 1 hr. The resultant was cooled slowly and filtered. The solid, beautiful red-reflecting, blue-transmitting needles, was washed with water, acetone, and hexane, and dried (0.48 g). A portion of it was recrystallized from dry tetrahydronaphthalene, washed with hexane and acetone, and dried at 140°C in the air and 110°C under vacuum. This gave the siloxane as tiny red-reflecting blue-transmitting crystals. NMR (CDCl_3): δ -2.98 (s, Me), -1.44 (s, t-Bu), 8.32 (m, 4,5 Pc), and 9.61 ppm (m, 3,6 Pc).

Anal. Calcd. for $\text{C}_{44}\text{H}_{46}\text{N}_8\text{O}_2\text{Si}_3$: C, 65.80; H, 5.77; Si, 10.49. Found: C, 66.05; H, 5.51; Si, 10.19.

The solubility of this compound in common organic solvents is very low.

ACKNOWLEDGMENTS

The authors thank the Office of Naval Research for support of this work.

REFERENCES

1. L. H. Sommer and L. J. Tyler, J. Am. Chem. Soc., 76, 1030 (1954).
2. E. J. Corey and A. Venkateswarlu, J. Am. Chem. Soc., 94, 6190 (1972).
3. L. H. Sommer and F. J. Evans, J. Am. Chem. Soc., 76, 1186 (1954).
4. H. A. Butlerow, Ann., 177, 176 (1875).
5. S. L. Douglass, Ph.D. Thesis, Case Western Reserve Univ., Cleveland, O., 1975.

TECHNICAL REPORT DISTRIBUTION LIST

	<u>No. Copies</u>		<u>No. Copies</u>
Office of Naval Research Arlington, Virginia 22217 Attn: Code 472	2	Defense Documentation Center Building 5, Cameron Station Alexandria, Virginia 22314	12
Office of Naval Research Arlington, Virginia 22217 Attn: Code 102IP	6	U.S. Army Research Office P.O. Box 12211 Research Triangle Park, NC 27709 Attn: CRD-AA-IP	1
ONR Branch Office 536 S. Clark Street Chicago, Illinois 60605 Attn: Dr. George Sandoz	1	Commander Naval Undersea Research & Development Center San Diego, California 92132 Attn: Technical Library, Code 133	1
ONR Branch Office 715 Broadway New York, New York 10003 Attn: Scientific Dept.	1	Naval Weapons Center China Lake, California 93555 Attn: Head, Chemistry Division	1
ONR Branch Office 1030 East Green Street Pasadena, California 91106 Attn: Dr. R. J. Marcus	1	Naval Civil Engineering Laboratory Port Hueneme, California 93041 Attn: Mr. W. S. Yanes	1
ONR Branch Office 760 Market Street, Rm. 447 San Francisco, California 94102 Attn: Dr. P. A. Miller	1	Professor O. Heinz Department of Physics & Chemistry Naval Postgraduate School Monterey, California 93940	1
ONR Branch Office 495 Summer Street Boston, Massachusetts 02210 Attn: Dr. L. H. Peebles	1	Dr. A. L. Slafkosky Scientific Adviser Commandant of the Marine Corps (Code RD-1) Washington, D.C. 20380	1
Director, Naval Research Laboratory Washington, D. C. 20390 Attn: Library, Code 2029 (ONRL)	6	The Asst. Secretary of the Navy (R&D) Department of the Navy Room 4E736, Pentagon Washington, D.C. 20350	1
	1		
	1		
Commander, Naval Air Systems Command Department of the Navy Washington, D.C. 20360 Attn: Code 310C (H. Rosenwasser)	1	Dr. T. C. Williams Union Carbide Corp. Chemicals & Plastics Tarrytown Technical Center Tarrytown, New York 10591	1
Dr. M. Good Department of Chemistry University of New Orleans Lakefront New Orleans, Louisiana 70122	1	Dr. K. A. Reynard Horizons Inc. 23800 Mercantile Road Cleveland, Ohio 44122	1

Dr. R. Soulen, Director
Contrast Research Department
Pennwalt Corp.
900 First Avenue
King of Prussia, Pennsylvania 19406 1

Dr. A. G. MacDiarmid
Department of Chemistry
University of Pennsylvania
Philadelphia, Pennsylvania 19174 1

Dr. E. Hedaya
Union Carbide Corp.
Corporate Research Laboratory
Tarrytown Technical Center
Tarrytown, New York 10591 1

Dr. A. Rheingold
SUNY Plattsburg
Department of Chemistry
Plattsburg, New York 12901 1

Dr. C. Pittman
Dept. of Chemistry
University of Alabama
University, Alabama 35486 1

Dr. M. Kenney
Department of Chemistry
Case Western Reserve University
Cleveland, Ohio 44106 1

Douglas Aircraft Co.
3855 Lakewood Blvd.
Long Beach, California 90846
Attn: Technical Library
C1 290/36-84
AUTO-Sutton 1

NASA-Lewis Research Center
21000 Brookpark Road
Cleveland, Ohio 44135
Attn: Dr. T. T. Serafini, MS 49-1 1

Dr. J. Griffith
Naval Research Laboratory
Chemistry Section, Code 6120
Washington, D.C. 20375 1

Dr. G. Goodman
Globe-Union Inc.
5757 North Green Bay Avenue
Milwaukee, Wisconsin 53201 1

Dr. E. Fischer, Code 2853
Naval Ship Research and Development Center
Annapolis Division
Annapolis, Maryland 21402 1

Dr. Martin H. Kaufman, Head
Materials Research Branch (Code 4542)
Naval Weapons Center
China Lake, California 93555

Dr. H. Allcock
Pennsylvania State University
University Park, Pennsylvania 16802 1

Dr. R. Lenz
Department of Chemistry
University of Massachusetts
Amherst, Massachusetts 01002 1

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER Technical Report No. 4 ✓	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) A Series of <u>tert</u> -Butyldimethylsiloxanes of Increasing Steric Hindrance		5. TYPE OF REPORT & PERIOD COVERED
7. AUTHOR(s) George W. Ritter, II, Malcolm E. Kenney		6. PERFORMING ORG. REPORT NUMBER
9. PERFORMING ORGANIZATION NAME AND ADDRESS Chemistry Department Case Western Reserve University Cleveland, Ohio 44106 ✓		8. CONTRACT OR GRANT NUMBER(s) N00014-75-C-0693 ✓
11. CONTROLLING OFFICE NAME AND ADDRESS ONR Branch Office 536 South Clark Street Chicago, Illinois 60605		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office) Chemistry Program Code 472 Office of Naval Research 800 N. Quincy St. Arlington, VA 22217		12. REPORT DATE Dec. 9, 1977
		13. NUMBER OF PAGES 6
		15. SECURITY CLASS. (of this report) Unclassified
16. DISTRIBUTION STATEMENT (of this Report) "Approved for public release; distribution unlimited"		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Siloxanes, Silicones, Phthalocyanines, Silicon, Steric Hindrance		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) Reaction of bis(dimethylsilyl)acetamide with <u>tert</u> -butyldimethylsilanol has been found to give 1- <u>tert</u> -butyl-1,1,3,3-tetramethyldisiloxane while reaction of bis(trimethylsilyl)acetamide or trimethylchlorosilane with this silanol has been found to give 1- <u>tert</u> -butyl-1,1,3,3,3-pentamethyldisiloxane. Likewise reaction of <u>tert</u> -butyldimethylchlorosilane with this silanol has been found to produce 1,3-di- <u>tert</u> -butyl-1,1,3,3-tetramethyldisiloxane and reaction of <u>tert</u> -butyl-dimethylchlorosilane with phthalocyaninosilanediol has been found to produce		

1,5-tert-butyl-1,1,5,5-tetramethyl-3-phthalocyaninotrisiloxane. This last siloxane is noteworthy because it is highly hindered.